

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
ACETALDEHYDE	RARE	○	○	○
ACETALDEHYDE	TR	◐	–	–
ACETEPHENON	TR	●	●	–
ACETIC ACID ANHYDRIDE	TR	●	–	–
ACETIC ACID, DILUTED	TR	●	◐	○
ACETIC ACID, DILUTED	40%	●	●	–
ACETONE	TR	●	–	–
ACID-ACETANHYDRIDE	40%	●	●	–
ACRILONITRILE	TR	●	◐	–
ADIPIC ACID	TR	●	●	–
AIR	TR	●	●	●
ALAUNE ME - ME III SULPHATE	GL	●	●	–
ALLYL ALCOHOL, DILUTED	96%	●	●	–
ALUM	GL	●	●	–
ALUMINIUM CHLORIDE	GL	●	●	–
ALUMINIUM SULPHATE	GL	●	●	–
AMBER ACID	GL	●	●	–
2-AMINO-ETHANOL	TR	●	–	–
AMMONIA, GAS	TR	●	●	–
AMMONIA, LIQUID	TR	●	●	–
ANILIN	TR	●	–	–
AMMONIA, WATER	GL	●	●	–
AMMONIUM ACETATE	GL	●	●	–
AMMONIUM CARBONATE	GL	●	●	–
AMMONIUM CHLORIDE	GL	●	●	–
AMMONIUM FLORIDE	L	●	●	–
AMMONIUM NITRATE	GL	●	●	●
AMMONIUM PHOSPHATE	GL	●	●	●
AMMONIUM SULPHATE	GL	●	●	●
AMYL ACETATE	TR	◐	–	–
AMYL ALCOHOL	TR	●	●	●
ANILINE	TR	◐	◐	–
ANILIN HYDROCHLORIDE	GL	●	●	–
ANON	TR	◐	◐	–
ANON (CYCLOHEXANONE)	TR	◐	◐	○
ANTIFREEZE	H	●	○	●
ANTIMONY TRICHLORIDE	90%	●	●	–
APPLE ACID/ЈАБОЛКОВ ОЛЈЕТ	L	●	●	–
APPLE ACIDS/ЈАБОЛКОВ ОЛЈЕТ	GL	●	●	–
APPLE WINE (ORTHO)	H	●	●	–
AQUA REGIA	H	●	●	●
ARSENIC ACID	40%	●	●	–
ARSENIC ACID	80%	●	●	◐
BARIUM HYDROXIDE	GL	●	●	●

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
BARIUM SALTS	GL	●	●	●
BATTERY ACID	H	●	●	–
BEER	H	●	●	●
BENZALDEHYDE	GL	●	●	–
BENZINE - BENZOL MIXTURE	8090/2090	◐	○	○
BENZOL	TR	◐	○	○
BENZIL CHLORIDE	TR	◐	–	–
BORAX	L	●	●	–
BORIC ACID	GL	●	●	●
BROMINE	TR	○	○	○
BROMINE VAPOURS	ALL	◐	○	○
BUTADIENE, GAS	TR	◐	○	○
BUTANE (2)DIOL(1,4)	TR	●	●	–
BUTANEDIOL	TR	●	●	–
BUTANETRIOL(1,2,4)	TR	●	●	–
BUTIN(2)DIOL(1,4)	TR	●	–	–
BUTYL ACETATE	TR	◐	○	○
BUTYL ALCOHOL	TR	●	◐	◐
BUTYL PHENOL	GL	●	–	–
BUTYL PHENON	TR	◐	–	–
BUTYLENE GLYCOL	10%	●	●	●
BUTYLENE GLYCOL	TR	●	●	●
BUTYLENE, LIQUID	TR	●	●	●
CALCIUM CABONATE	GL	●	–	–
CALCIUM CHLORIDE	GL	●	●	–
CALCIUM HYDROXIDE	GL	●	–	–
CALCIUM HYPOCHLORITE	L	●	●	–
CALCIUM NITRATE	GL	●	●	–
CARBOLINE	H	●	●	–
CARBON DIOXIDE, GAS	ALL	●	●	–
CARBONDIOXIDE, LIQUID	ALL	○	○	○
CARBONHYDRIDE	RARE	●	●	●
CARBONIMONOXIDE	ALL	●	●	–
CARBONSULPHIDE	TR	●	–	–
CAUSTIC SODA	60%	●	●	–
CHLORAL	TR	●	◐	○
CHLORAMINE	L	●	◐	○
CHLORETHANOL	TR	●	○	○
CHLORIC ACID	1%	◐	–	–
CHLORIC ACID	10%	○	○	○
CHLORIC ACID	20%	◐	○	○
CHLORINE	0.5%	○	○	○
CHLORINE	1%	○	○	○
CHLORINE	GL	◐	○	○

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
CHLORINE, GAS	TR	○	○	○
CHLORINE, WATER	TR	○	○	○
CHLOROACETIC ACID	L	●	●	—
CHLOROBENZOL	TR	⦿	—	—
CHLOROFORM	TR	⦿	○	○
CHLOR SULPHON ACID	TR	○	○	○
CHROMIC ACID	40%	⦿	⦿	○
CHROMIC ACID/SULPHURIC ACID/WATER	15/35/50%	○	○	○
CHROTONIC ALDEHYDE	TR	●	—	—
CITRIC ACID	VL	●	●	●
CITRIC ACID	VL	●	●	●
CITY GAS	H	●	—	—
COCONUT FAT ALCOHOL	TR	●	⦿	—
COCONUT OIL	TR	●	—	—
COGNAC	H	●	●	—
COPPER(II)CHLORIDE	GL	●	●	—
COPPER(I)CYANIDE	GL	●	●	—
COPPER(III) NITRATE	30%	●	●	●
COPPER SULPHATE	GL	●	●	—
CORN OIL	TR	●	⦿	—
COTTON OIL	TR	●	●	—
CRESOL	90%	●	●	—
CRESOL	>90%	●	—	—
CYCLOHEXANE	TR	●	—	—
CYCLOHEXANOL	TR	●	⦿	—
CYCLOHEXANONE	TR	⦿	○	○
DEXTRINE	L	●	●	—
DEXTRINE	L	●	●	—
DEXTROSE	20%	●	●	●
1,2 DIAMINOETHAN	TR	●	●	—
DICHLORO ACETIC ACID	TR	⦿	—	—
DICHLORO ACETIC ACID	50%	●	●	—
DICHLORO BENZENE	TR	⦿	—	—
DICHLORO ETHYLENE (1,1-1,2)	TR	⦿	—	—
DIESEL OIL	H	●	⦿	—
DIETHYL AMINE	TR	●	—	—
DIETHYL ETHER	TR	●	⦿	—
DIGLYCOLIC ACID	GL	●	●	—
DIHEXYL PHATALATE	TR	●	⦿	—
DI-ISO OCTYLPHATALATE	TR	●	⦿	—
D-ISO PROPYLETHER	TR	⦿	○	—
DIMETHYFORMAMIDE	TR	●	●	—
DYMETHYL AMINE	100%	●	—	—
DI-N BUTYL ETHER	TR	⦿	—	—

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
DINONYL PHATALATE	TR	●	⦿	—
DIOCTYL PHATALATE	TR	●	⦿	—
DIOXANE	TR	⦿	⦿	—
DRINKING WATER	TR	●	●	●
ETHANOL	L	●	—	—
ETHANOL+2% TOLUENE	96%	●	—	—
ETHYL ACETATE	TR	●	⦿	○
ETHYL ALCOHOL	TR	●	●	●
ETHYL BENZOL	TR	⦿	○	○
ETHYL CHLORIDE	TR	○	○	○
ETHYLENE DIAMINE	TR	●	●	—
ETHYLENE GLYCOL	TR	●	●	●
ETHYLENE OXIDE	TR	○	—	—
FATTY ACID	20%	●	—	—
FATTY ACIDS>C4	TR	●	⦿	—
FERMENTATION MALT	H	●	●	—
FERTILIZER SALTS	GL	●	●	—
FILM BATH	H	●	●	—
FLUORINE	TR	⦿	—	—
FLUOSILICIC ACID	32%	●	●	—
FORMALDEHYDE	40%	●	●	—
FORMIC ACID	10%	●	●	⦿
FORMIC ACID	85%	●	⦿	○
FRUCTOSE	L	●	●	●
FRUIT WUICES	H	●	●	●
FURFURYL ALCOHOL	TR	●	⦿	—
GELATINE	L	●	●	●
GLUCOSE	20%	●	●	●
GLYCERINE	TR	●	●	●
GLYCOLIC ACID	30%	●	⦿	—
GREASE	H	⦿	—	—
HCL/HNO3	75/25%	○	○	○
HEPTANE	TR	●	⦿	○
HEXANE	TR	●	⦿	—
HEXANETRIOL (1,2,6)	TR	●	●	—
HYDRAZINE HUDRATE	TR	●	—	—
HYDROBROMINE ACID	48%	●	⦿	○
HYDROCHLORIC ACID	20%	●	●	—
HYDROCHLORIC ACID	20-36%	●	⦿	⦿
HYDROFLUORIC ACID	40%	●	●	—
HYDROFLUORIC ACID	70%	●	⦿	—
HYDROGEN	TR	●	●	—
HYDROGEN CHLORIDE	TR	●	●	—
HYDRGEN PROXIDE	30%	●	⦿	—

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
HYDROSYANIC ACID	TR	●	●	–
HYDROXYLAMMONIUM SULFATE	12%	●	●	–
IODINE SOLUTION	H	●	●	–
ISOOCTANE	TR	●	●	○
ISOPROPYL	TR	●	●	●
KEROSEN	H	●	●	○
LASTIC ACID	90%	●	●	–
LANOLIN	H	●	●	–
LEAD ACETATE	GL	●	●	○
LINSEED OIL	H	●	●	●
LUBRICATING OILS	TR	●	●	○
MAGNESIUM CHLORIDE	GL	●	●	●
MAGNESIUM HYDROCARBONATE	GL	●	○	○
MAGNESIUM SALTS	GL	●	●	–
MAGNESIUM SULPHATE	GL	●	●	●
MENTHOL	TR	●	●	–
METHANOL	TR	●	●	–
METHANOL	5%	●	●	●
METHYL ACETATE	TR	●	●	–
METHYL AMINE	32%	●	–	–
METHYL BROMIDE	TR	○	○	○
METHYL CHLORIDE	TR	○	○	○
METHYL ETHYL KETONE	TR	●	●	–
MERCURY	TR	●	●	–
MERCURY SALTS	GL	●	●	–
MILK	H	●	●	●
MINERAL WATER	H	●	●	●
MOLASSES	H	●	●	●
MOTOR OIL	TR	●	●	–
NATURAL GAS	TR	●	–	–
NICKEL SALTS	GL	●	●	–
NITRIC ACID	10%	●	●	○
NITRIC ACID	10-50%	●	○	○
NITRIC ACID	>50%	○	○	○
2-NITROTOLUEN	TR	●	●	–
NITROUS GASES	ALL	●	●	–
OLEUM(H2SO4+SO3)	TR	○	○	○
OLIVE OIL	TR	●	●	●
OXALIC ACID	GL	●	●	○
OXYGEN	TR	●	–	–
OZONE	0,5PPM	●	●	–
PARAFFIN EMULSIONS	H	●	●	–
PARAFFIN OIL	TR	●	●	○
PERCHLORIC ACID	20%	●	●	–

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
PERCHLOROETHYLENE	TR	●	●	–
PETROLEUM	TR	●	●	–
PETROLEUM ETHER	TR	●	●	–
PHENOL	5%	●	●	–
PHENOL	90%	●	–	–
PHENYL HYDRAZINE	TR	●	●	–
PHENYL HYDRAZINE HYDROCHLORIDE	TR	●	●	–
PHOSGENE	TR	●	●	–
PHOSPHATES	GL	●	●	–
PHOSPHORIC ACID	85%	●	●	●
PHOSPHORUS OXYCHLORIDE	TR	●	–	–
PHTHALIC ACID	GL	●	●	–
PHOTO EMULSIONS	H	●	●	–
PHOTO FIXING BATHS	H	●	●	–
PICRIC ACID	GL	●	–	–
POTASSIUM BICHROMATE	GL	●	●	–
POTASSIUM BROMATE	10%	●	●	–
POTASSIUM BROMIDE	GL	●	●	–
POTASSIUM CARBONATE	GL	●	●	–
POTASSIUM CHLORATE	GL	●	●	–
POTASSIUM CHLORIDE	GL	●	●	–
POTASSIUM CHROMATE	GL	●	●	–
POTASSIUM CYANIDE	L	●	●	–
POTASSIUM FLUORIDE	GL	●	●	–
POTASSIUM HYDROGEN CARBONATE	GL	●	●	–
POTASSIUM HYDROXIDE	50%	●	●	●
POTASSIUM IODIDE	GL	●	●	–
POTASSIUM NITRATE	GL	●	●	–
POTASSIUM PERCHLORATE	10%	●	●	–
POTASSIUM PERMANGANATE	GL	●	○	–
POTASSIUM PERSULFATE	GL	●	●	–
POTASSIUM SULFATE	GL	●	●	–
PROPANE, GAS	TR	●	–	–
PROPANOL (I)	TR	●	●	–
PROPARGYL ALCOHOL	7%	●	●	–
PROPIONIC ACID	>50%	●	–	–
PROPYLENE GLYCOL	TR	●	●	–
PYRIDIN	TR	●	●	–
SEAWATER, BRINE	H	●	●	●
SILICIC ACID	All	●	●	–
SILICO FLUORIC ACID	32%	●	●	–
SILICONE EMULSION	H	●	●	–
SILICONE OIL	TR	●	●	●

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
SILVER NITRATE	GL	●	●	⦿
SILVER SALTS	GL	●	●	—
SODIUM ACETATE	GL	●	●	●
SODIUM BENZOATE	35%	●	●	—
SODIUM BICARBONATE	GL	●	●	●
SODIUM BISULPHATE	GL	●	●	—
SODIUM BISULPHITE	L	●	—	—
SODIUM CARBONATE	50%	●	●	⦿
SODIUM CHLORATE	GL	●	●	—
SODIUM CHLORIDE	VL	●	●	●
SODIUM CHLORITE	VL	●	●	●
SODIUM CHLORITE	2-20%	●	⦿	○
SODIUM CHROMATE	GL	●	●	●
SODIUM HYDROX	60%	●	●	●
SODIUM HYPOCHLORIDE	20%	○	○	○
SODIUM HYPOCHLORITE	10%	●	—	—
SODIUM HYPOCHLORITE	20%	⦿	⦿	○
SODIUM NITRATE	GL	●	●	—
SODIUM SILICATE	L	●	●	—
SODIUM SULPHATE	GL	●	●	—
SODIUM SULPHIDE	GL	●	●	—
SODIUM SULPHIDE	40%	●	●	●
SODIUM THIOSULPHATE	GL	●	●	—
SODIUM TRIPHOSPHATE	GL	●	●	●
SAYABEAN OIL	TR	●	⦿	—
STRACH SOLUTION	All	●	●	—
STRACH SYRUP	All	●	●	—
SULPHURDIOXIDE	All	●	●	—
SULPHURDIOXIDE, GAS	TR	●	●	—
SULPHURDIOXIDE, LIQUID	All	●	●	—
SULPHURIC ACID	10%	●	●	●
SULPHURIC ACID	10-80%	●	●	—
SULPHURIC ACID	80%-TR	⦿	○	—
SULPHURIC ACID		○	○	○
SULPHURIC ACID	All	●	●	—
SULPHUR TRIOXIDE	All	●	●	—
TAR OIL	H	●	○	○
TETRACHLOROETHANONE	TR	⦿	○	○
TETRACHLOROETHYLENE	TR	⦿	⦿	—
TETRACHLOROMETHANE	TR	○	○	○
TETRAETHYL LEAD	TR	●	—	—
TETRAHYDROFURANE	TR	⦿	○	○
TETRAHYDRONAPHATALENE	TR	○	○	○
THIONYL CHLORIDE	TR	⦿	○	○

АГРЕСИВНИ СРЕДСТВА	КОН-ЦЕН-ТРА-ЦИЈА	ХЕМИСКА ОТПОРНОСТ		
		20°C	60°C	100°C
TIN (II) CHLORIDE	GL	●	●	—
TIN (IV) CHLORIDE	GL	●	●	—
TOULENE	TR	⦿	○	○
TRICHLOROETHYLENE	TR	○	○	○
TRICHLORO ASETIC ACID	50%	●	●	—
TRICRESYL PHOSPHATE	TR	●	⦿	—
TRIETHANOLAMIN	L	●	—	—
WINE VINEGAR	H	●	●	●
XYLENE	TR	⦿	○	○
YEAST	ALL	●	—	—
ZINK	GL	●	●	—
TRIOCTYL PHOSPHATE	TR	●	—	—
UREA	GL	●	●	—
VASELINE OIL	TR	●	⦿	—
VINEGAR	H	●	●	●
VINYL ACETATE	TR	●	⦿	—
WASHING POWDER	VL	●	●	—
WASTE GASES CONTAINING HYDROGEN FLUORIDE	RARE	●	●	—
WATER, PURE	H	●	●	●
WAX	H	●	⦿	—
WINE ACID	10%	●	●	—
WINES	H	●	●	—